Perlast G75B

Black multi-purpose high temperature perfluoroelastomer compound

PERLAST®

Description

Perlast G75B offers a unique blend of excellent chemical resistance, mechanical properties and high temperature stability, simultaneously extending the operating limits in all three aspects.

Perlast® G75B has been specially formulated to provide increased acid resistance by eliminating fillers that are prone to acid attack and optimising the polymer structure. In addition, this perfluoroelastomer has low permeability and as a result, it is less prone to swelling, leading to extended in-service performance in, for example, valves, pumps and mechanical seals.

A high modulus makes Perlast G75B resistant to extrusion and ideal for use in medium-high pressure applications. In addition, the low cumulative compression set provides a high mean-time between maintenance cycles in hot chemically aggressive environments.

Perlast® G75B is suitable for both dynamic and static applications and can be fully moulded into O-rings (any size up to 2m/6.5ft internal diameter) and custom shapes.

Key Attributes

- Excellent chemical resistance to a wide range of chemicals
- Exceptional acid and amine resistance
- Superior mechanical properties
- Long-term sealing efficiency at high temperature
- Extremely low out-gassing properties
- ▶ Good steam resistance (ASME BPE 2000)
- Less than 2% swell in MIL-L-23699C jet oil after 336 hours at 200°C

Typical Applications

Aerospace – Inter-stage seal assemblies (static O-rings)

Chemical Processing - Pumps

Valves

Mechanical seals

Diesel – Pre-heat chambers

Exhaust valve seats

Semiconductor – Gas abatement systems (static)


High temperature environments

Oil & Gas – High temperature down-hole environments

Electrical bulkhead feed-throughs

Other materials in this range

Perlast G75H (white high temperature up to +320°C/+608°F)
Perlast G75TX (black high temperature up to +327°C/+621°F)
Perlast G75M (black multi-purpose up to +260°C/+500°F)



Typical Material Properties

| Property | ASTM | ISO | Value |
|--|-------|---------|----------------------|
| Material Type | FFKM | FFPM | |
| Colour | | | Black |
| Hardness: (°IRHD) | D1415 | ISO48 | 78 |
| (Shore A) | D2240 | ISO7619 | 79 |
| Tensile Strength (MPa) | D412 | ISO37 | 19.2 |
| Elongation at break (%) | D412 | ISO37 | 160 |
| 100% Modulus (MPa) | D412 | ISO37 | 12.0 |
| Compression Set: 72 hrs @ 200°C (392°F) | D395 | ISO815 | 18.0 |
| Minimum Operating Temperature | | | -15°C (+5°F) |
| Maximum Operating Temperature | | | +325°C (+617°F) |
| Coefficient of Thermal Expansion (°C-1) | | | 4.0x10 ⁻⁴ |



Corporate Headquarters 4015 Casilio Parkway Clarence, New York 14031 Ph: 716-759-2222 • Fax 716-759-6425



Canadian Division 5511 Steeles Ave West • Unit 5 North York, Ontario M9L 1S7 Ph: 416-741-0750 • Fax: 416-741-0230