

RoHS Complaint

Epoxy RHS-0525

Operating Temperature	-100 to 130 °C
Cure	1.5 hours @ 70°C
Shore Hardness, Durometer D	95
Density	2.4 g/cm ³
Water Absorption 24 hrs @ RT	0.03%
Compressive Strength	22,700 PSI
Dielectric Strength	14.8 kV/mm
Outgassing	0.28% TML, 0.02% CVCM, 0.08% WVR

Manufacturer certifies that the product listed above is RoHS compliant.

Manufacturer certifies that the product listed above do not contain Substances of Very High Concern (SVHC) above the 0.1% w/w threshold values as defined in Article 57 of Regulation (EC) No 1907/2006, the REACH Regulation.

Manufacturer certifies that the product listed above does not contain Dechlorane Plus.